



Kut Gard®

Seamless Knit DuPont™ Kevlar® Glove - Heavy Weight

- Kevlar® provides excellent cut protection, heat resistance and is inherently flame resistant
- Seamless knit construction protects hands without sacrificing comfort or dexterity
- Knit Wrist helps prevent dirt and debris from entering the glove
- Reversible design allows replacing one glove at a time, rather than pairs
- Can be used as gloves or glove liners
- Color coded hems for easy size identification

Applications

- Cut Resistance with Light Heat Protection
- Automotive Applications
- Glass Operations



Technical Data

Color	Yellow
Sizes Available	XS - XL
Packaging	Bulk Pack
Packed	6/Case
Case Dimensions (in)	18.00 x 12.00 x 12.00
Case Weight (lbs)	13.01
Country of Origin	United States
Liner Material	Kevlar
Coating	Uncoated
Gauge	7
Cuff	Knit Wrist
Hide	--
Impact Protection	--
Construction	Seamless Knit
Certifications	TAA Compliant
Product Circularity	Recycled via Terracycle Reusable / Launderable

Performance Data

Cut Level	A3
ANSI Abrasion Level	--
ANSI Puncture Level	--
ANSI Impact Level	--
ANSI Contact Heat Level	2
EN 388	--
ASTM F1358 Vertical Flame Level	--
EN 407	--

Care Instructions



Machine
Wash



Water Temp
55°C



Do Not
Bleach



Tumble Dry



Medium Heat

KEY: Made from recycled or bio-based Launderable Recyclable via TerraCycle®

PROTECTIVE INDUSTRIAL PRODUCTS, INC. | BRINGING THE BEST OF THE WORLD TO YOU®

AMERICAS: +1 (800) 262-5755 | EUROPE: +34-96182-41-48 | AMEA: (ASIA, MIDDLE EAST, AFRICA) 852-2475-9228 | www.pipglobalsafety.com

This document and the information contained herein is the property of Protective Industrial Products, Inc. (PIP) and may not be used or reproduced without permission. Product users should conduct all appropriate testing or other evaluations to determine the suitability of PIP products for a particular purpose or use within a particular environment. PIP DISCLAIMS ALL WARRANTIES OTHER THAN AS EXPRESSLY PROVIDED. 2025-05-12



SKU Information

SKU	COLOR	SIZE	UPC	UPC (INNER)	UPC (CASE)
-----	-------	------	-----	-------------	------------



WORLDWIDE®
PROTECTIVE PRODUCTS

PHYSICAL TESTING AND APPLICATIONS LABORATORY

Test # 21-522

1409 Worldwide Lane
Wilkesboro, NC 28697
Tel: 716-825-0808
Fax: 716-332-9280

ABRASION RESISTANCE TEST RESULTS (TABER METHOD)

The following results were obtained using the standards set forth by the American Society for Testing and Materials (ASTM) under the fixed designation:

ASTM D3884-09

This test was performed on a properly calibrated Taber Industries Abraser using all the methods and materials as stated within the ASTM standard.

The ASTM D 3389-10 results are: **700** Cycles to Hole

ANSI / ISEA 105-2016 rating is: **Level 2**

Product ID =

07-K350

Product Description=

7G Kevlar Glove

Test ID # =

21-522

Testing Date =

August 18, 2021

Instrument	Taber Ind. Rotary Abraser 5135
Calibration Certification #:	20081632-08-18
Standard Used	ASTM D3884-09
Weight Applied	500g
Material	As Supplied - Unused
Conditioning	In accordance w/ Practice D1776
Wheel Reface Schedule	Every 10000 cycles
Wheel Type	H-18

ANSI / ISEA 105-2005 Ratings	
Level 0	< 100 cycles
Level 1	≥ 100 cycles
Level 2	≥ 500 cycles
Level 3	≥ 1000 cycles
Level 4	≥ 3000 cycles**
Level 5	≥ 10000 cycles**
Level 6	≥ 20000 cycles**

** Note: Ratings 0-3 are using 500g and ratings 4-6 are using 1000g

of Cycles to Fail Point (per each specimen)

Specimen # 1	700
Specimen # 2	
Specimen # 3	
Specimen # 4	
Specimen # 5	

Final test result (seen above in red) is obtained by calculating the average of the test results for all specimens tested to the left.

Worldwide Protective Products LLC certifies that the following test was performed in accordance with the specification test requirements and that the reported results are true and valid.

This report is limited and related only to the particular instrument, material or other subject to which it refers. These test results can not be compared to results obtained using different methods or under different conditions. No representation is made that similar articles will be of like quality.

ISEA Cut Resistance Performance Calculator

Manufacturer	WWP		Test #	A1540-21
Product Name	07-K350			
Product Type	7G Kevlar Glove			
Test Date	8/17/2021	Test Lab/Facility	WPP R&D Laboratory	
Temperature	72	Humidity	45%	Operator
			KR	

Average Rating Force
(gf)**1267**

1 Samples Tested

ASTM F2992-15

TDM-100

Cut Resistance
Performance Level**A3**

ANSI/ISEA 105-2016

Section 5.1.1

Sample 1					Sample 2 <input type="checkbox"/> Include					Sample 3 <input type="checkbox"/> Include					
Rating Force (gf)					Rating Force (gf)					Rating Force (gf)					
1267															
Load (gf)					Load (gf)					Load (gf)					
Norm. Distance (mm)					Norm. Distance (mm)					Norm. Distance (mm)					
No Cut					No Cut					No Cut					
Calibration Cut (before)					500	20.42				500			500		
Sample Cuts	1	1200	50.00	48.26	*	1200				1200					
	2	1200	34.23	33.04		1200				1200					
	3	1200	39.72	38.34		1200				1200					
	4	1200	36.39	35.13		1200				1200					
	5	1200	43.72	42.20		1200				1200					
	6	1250	21.87	21.11		1250				1250					
	7	1250	21.97	21.21		1250				1250					
	8	1250	23.92	23.09		1250				1250					
	9	1250	22.14	21.37		1250				1250					
	10	1250	22.75	21.86		1250				1250					
	11	1300	17.38	16.78		1300				1300					
	12	1300	13.67	13.19		1300				1300					
	13	1300	7.86	7.59		1300				1300					
	14	1300	16.75	16.17		1300				1300					
	15	1300	19.41	18.74		1300				1300					
Calibration Cut (after)					500	21.02				500					
					Sharpness Correction	0.97				Sharpness Correction	1.00				
					Reference Distance	20.00 mm				Reference Distance	20.00 mm				
					Rating Force	1267.26 gf				Rating Force	gf				
					95% Confidence Interval	38.64 gf				95% Confidence Interval	gf				
					Standard Deviation	17.88 gf				Standard Deviation	gf				
					R-Squared	0.87				R-Squared					
					Correction Factor	0.06				Correction Factor					
					Basis Weight	678.1 g/sq.m.				Basis Weight	523.1 g/sq.m.				
					Thickness	mm				Thickness	mm				
					Sample Weight	3.500 2" x 4"				Sample Weight	2.700 2" x 4"				
					Oz. per Sq. Yard	20.000				Oz. per Sq. Yard	15.429				
Optional Sample Properties															